

## TECHNICAL DATA

### Teijin® Tetoron® Films

#### U2

#### ■ Characteristics

Opaque matte white film

#### ■ Typical Applications

White board, magnetic Card

#### ■ Pretreatment

Adhesion Promotion, Anti-static & adhesion Promotion

#### ■ Technical Data

Item		Unit	U2 Type							Test method
Thickness		μm	38	50	75	100	125	188	250	JIS C2151
Tensile strength	MD	MPa	180	180	180	180	170	160	160	JIS C2318
	TD		210	210	210	200	190	160	160	
Tensile elongation	MD	%	110	110	120	120	120	110	110	JIS C2318
	TD		80	80	90	100	100	100	100	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	%	1.1	1.1	1.1	1.1	1.1	1.1	1.1	JIS C2318
	TD		0.3	0.3	0.2	0.2	0.1	0.1	0.1	

- 1.The information contained herein is believed to be reliable and correct.
- 2.Please refer to the MSDS for product safety data.
- 3.Information is presented without guarantee or warranty.