



# DuPont Teijin Films™

Welcome, Chris Pendlebury Current Language: **US**

[Logoff](#) | 
 [Welcome Page](#) | 
 [Film Type Selector](#) | 
 [Market Locator](#) | 
 [Product Locator](#)

[Show Printable Version](#)

## MELINEX® ST329

DTF Only - Active

### Product Description

MELINEX® ST329 has good handling properties and a unique pearlescent appearance with no pre-treatments. It is heat stabilized for applications in high temperature processes where film registration is critical.

### Typical Properties

<b>Available Thickness [Gauge]</b>
300; 1000

Property	Thickness	Value	Units	Test
<b>OPTICAL</b>				
Optical Density	1000	1.20		ASTM D1003
Total Light Transmission (TLT)	300	14.0	%	ASTM D1003
Total Light Transmission (TLT)	1000	4.5	%	ASTM D1003
Whiteness	ALL	100	%	ASTM E313-79
<b>PHYSICAL</b>				
C.O.F. (static)	ALL	0.32		ASTM D1894
Tensile Strength MD (break)	300	17,500	psi	ASTM D882A
Tensile Strength MD (break)	1000	16,000	psi	ASTM D882A
Tensile Strength TD (break)	300	21,000	psi	ASTM D882A
Tensile Strength TD (break)	1000	19,000	psi	ASTM D882A
<b>THERMAL</b>				
Shrinkage MD (150°C)	ALL	0.07	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	ALL	0.02	%	Unrestrained @ 150°C/30 min

### Contact Info

DuPont Teijin Films U.S. Limited Partnership  
 3600 Discovery Drive  
 Chester, VA 23836 USA  
 Tel: (800) 635-4639  
 Fax: (804) 530-9867

### Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont

Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetonex® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.



[Show Printable Version](#)

Copyright © 2006 DuPont Teijin Films. All rights reserved.  
Developed and Powered by Client Centered Technologies, Inc.