




# DuPont Teijin Films™

## MYLAR® OWF

### Product Description

Mylar® OWF is a co-extruded, one side amorphous, heat sealable polyester film designed to be used as an overwrap film. This film is suitable for use in contact with food.



### Approvals

**Food Contact Status** - Please contact your DuPont Teijin Films representative to receive the Regulatory Compliance documents

### Typical Properties

Available Thickness [Gauge]
48; 80; 120

Property	Thickness	Value	Units	Test
<b>BARRIER</b>				
Gas Permeability - O <sub>2</sub> , 24 hr	48	6.0	cc/100 in <sup>2</sup>	ASTM D1434 77°F/75% RH/1 ATM
Gas Permeability - O <sub>2</sub> , 24 hr	80	3.7	cc/100 in <sup>2</sup>	ASTM D1434 77°F/75% RH/1 ATM
WVTR	48	2.8	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 90% RH
WVTR	80	1.8	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 90% RH
<b>OPTICAL</b>				
Haze	48	3.0	%	ASTM D1003
Haze	80	4.5	%	ASTM D1003
Haze	120	6.0	%	ASTM D1003
Total Light Transmission (TLT)	48	88.7	%	ASTM D1003
Total Light Transmission (TLT)	80	88.6	%	ASTM D1003
Total Light Transmission (TLT)	120	88.5	%	ASTM D1003
<b>PHYSICAL</b>				
C.O.F. (dynamic) A-B	48 - 80	0.5		ASTM D1894
Density	48 - 80	1.40	g/cc	
Elongation at Break MD	48 - 80	100	%	ASTM D882A
Elongation at Break TD	48 - 80	90	%	ASTM D882A
Tensile Strength MD	48 - 80	27	kpsi	ASTM D882A
Tensile Strength TD	48 - 80	29	kpsi	ASTM D882A
Yield (nominal)	48	42,200	in <sup>2</sup> /lb	
Yield (nominal)	80	24,800	in <sup>2</sup> /lb	
Yield (nominal)	120	16,500	in <sup>2</sup> /lb	
<b>THERMAL</b>				
Heat Seal Temp. Range	48 - 80	220-400	°F	
Shrinkage MD (150°C)	48 - 80	1.25	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	120	1.5	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	48 - 80	0.30	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	120	1.5	%	Unrestrained @ 150°C/30 min

**Contact Info**

DuPont Teijin Films U.S. Limited Partnership  
3600 Discovery Drive  
Chester, VA 23836 USA  
Tel: (800) 635-4639  
Fax: (804) 530-9867

**Disclaimer**

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Teton® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.