



# DuPont Teijin Films™

## MELINEX® 378

### Product Description

MELINEX® 378 is a translucent, matte, polyester film which has a rougher surface (lower surface gloss) than MELINEX® 377.

### Approvals

**UL Recognition** - Product has been registered with Underwriters Laboratories

### Typical Properties

<b>Available Thickness [Gauge]</b>
75; 92; 200

Property	Thickness	Value	Units	Test
<b>OPTICAL</b>				
Gloss 45 Degrees	All	18	%	ASTM D523
Gloss 60 Degrees	All	18	%	ASTM D523
Haze	75	90	%	ASTM D1003
Haze	92	94	%	ASTM D1003
Haze	200	96	%	ASTM D1003
Total Light Transmission (TLT)	75-92	78	%	ASTM D1003
Total Light Transmission (TLT)	200	64	%	ASTM D1003
<b>PHYSICAL</b>				
C.O.F. (dynamic) A-B	All	0.3		ASTM D1894
Elongation at Break MD	All	90	%	ASTM D882A
Elongation at Break TD	All	60	%	ASTM D882A
Tensile Strength MD	All	22,000	psi	ASTM D882A
Tensile Strength TD	All	28,000	psi	ASTM D882A
<b>THERMAL</b>				
Shrinkage MD (190°C)	75-92	2.5	%	Unrestrained @ 190°C/5 min
Shrinkage MD (190°C)	200	1.2	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)	75-92	0.0	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)	200	0.5	%	Unrestrained @ 190°C/5 min

### Contact Info

DuPont Teijin Films U.S. Limited Partnership  
3600 Discovery Drive  
Chester, VA 23836 USA  
Tel: (800) 635-4639  
Fax: (804) 530-9867

### Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture

products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.