



MYLAR® MO21

Product Description

Mylar® type MO21 films are strong, heavy gauge films that have excellent electrical properties. These films offer exceptional cut-through resistance, low shrinkage, low moisture absorption, and high thermal durability. Mylar® type MO21 films are used as insulation in systems that have been given Class B ratings by Underwriters Laboratories (UL). They also offer product uniformity that enhances processing on automatic slot and wedge insertion equipment.

General Product Info

The inherent mechanical durability of Mylar® type MO21 films and their good dielectric and thermal durability characteristics endow these films with multiple advantages in motors and generators.

Special Features

Slit rolls are available in the following ID and OD configuration:

- 3" ID 13" OD
- 3" ID 16" OD
- 3" ID 18" OD

Master rolls are available as shown in the Standard Put-Ups table. They are splice free and are available in selected widths in minimum order quantities of 35,000 lb per order with a minimum of 10,000 lb per item.

Typical Applications

Mylar® type MO21 films are being widely used for electrical insulation in slot liners, wedges and phase insulation for motors and generators. Mylar® type MO21 films are also frequently used in hermetic motor/compressor sealed units, fractional horse power motors, diaphragms, and industrial laminations.

Approvals

UL 94 VTM-2 - for 92-1400 gauge (0.023-0.35mm)

UL Recognition - for 92-500 gauge (0.023-0.35 mm) HWI=5, HAI=4, CTI=1;
for 700-1400 gauge (0.18-0.35mm) HWI=4, HAI=0, CTI=1

Typical Properties

Available Thickness [Gauge]
750; 900; 1000; 1400

Property	Thickness	Value	Units	Test
ELECTRICAL				
Dielectric Strength	750	17.5	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Dielectric Strength	900	18.4	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Dielectric Strength	1000	19.0	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Dielectric Strength	1400	20.0	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
OPTICAL				
Opacity	750	38	%	optical density
Opacity	900	41	%	optical density
Opacity	1000	42	%	optical density
Opacity	1400	46	%	optical density
PHYSICAL				
Density	750	1.3928	g/cc	
Density	900	1.3920	g/cc	

Density	1000	1.3925	g/cm3	
Density	1400	1.3925	g/cc	
Elongation at Break MD	750	140	%	ASTM D882A
Elongation at Break MD	900	150	%	ASTM D882A
Elongation at Break MD	1000	150	%	ASTM D882A
Elongation at Break MD	1400	170	%	ASTM D882A
Elongation at Break TD	750	115	%	ASTM D882A
Elongation at Break TD	900	130	%	ASTM D882A
Elongation at Break TD	1000	140	%	ASTM D882A
Elongation at Break TD	1400	170	%	ASTM D882A
Tensile Strength MD	750	27	kpsi	ASTM D882A
Tensile Strength MD	900	27	kpsi	ASTM D882A
Tensile Strength MD	1000	27	kpsi	ASTM D882A
Tensile Strength MD	1400	26	kpsi	ASTM D882A
Tensile Strength TD	750	30	kpsi	ASTM D882A
Tensile Strength TD	900	29	kpsi	ASTM D882A
Tensile Strength TD	1000	29	kpsi	ASTM D882A
Tensile Strength TD	1400	25	kpsi	ASTM D882A
Yield (nominal)	750	2,600	in ² /lb	
Yield (nominal)	900	2,200	in ² /lb	
Yield (nominal)	1000	2,000	in ² /lb	
Yield (nominal)	1400	1,400	in ² /lb	
THERMAL				
Shrinkage MD (150°C)	750	1.6	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	900	1.6	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	1000	1.5	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	1400	1.3	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	750	0.9	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	900	1.1	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	1000	1.1	%	Unrestrained @ 150°C/30. min
Shrinkage TD (150°C)	1400	0.8	%	Unrestrained @ 150°C/30 min

Standard Put-ups

Core I.D. (Inches)	Roll O.D. (Inches)	Thickness (Gauge)	Length (Feet)
3	13	750	1,360
3	13	900	1,140
3	13	1000	1,020
3	13	1400	730
10 (Master roll)		750	5,400
10 (Master roll)		900	4,520
10 (Master roll)		1000	4,070
10 (Master roll)		1400	2,850

Contact Info

DuPont Teijin Films U.S. Limited Partnership
3600 Discovery Drive
Chester, VA 23836 USA
Tel: (800) 635-4639
Fax: (804) 530-9867

Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S.

Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.